

TUF-TRAC® LINE STRIPING

SERIES A256
A TEXTURED, ACRYLIC LINE STRIPING



PORT BYRON, IL 61275 • (309) 523-2121
 1-800-747-1084 FAX# 1-309-523-3912

DESCRIPTION

SANPRO®TUF-TRAC® LINE STRIPING is specially formulated for surfaces with **SANPRO® TUF-TRAC®**. It is compatible with other coating systems, as well as asphalt and conditioned concrete. **TUF-TRAC® LINE STRIPING** creates sharp, bright lines that won't fade or peel and its heavy body helps prevent "feathering" under the tape during application.

TYPICAL USES

Line striping tennis courts, playgrounds, and parking lots that have been coated with **TUF-TRAC®**.

OUTSTANDING FEATURES/BENEFITS

- Excellent exterior durability
- Resistant to cracking
- Texturized for slip resistance on tennis courts

LIMITATIONS

- Applying at temperatures below 50°F will greatly prolong drying time.
- Protect from rain for at least 2 hours after application.
- Do not freeze. If frozen, move to a warm place until thawed. Check sample can for homogeneous viscosity. If paint has gelled or is too thick to apply, discard.

TYPE: Acrylic
COLORS: White
FINISH: Flat
PACKAGING: 1 gallon cans

NOTICE

Before using this product, read all warnings and safety information printed on the label, the Material Safety Data Sheet, and the Technical Information Guide.

SURFACE PREPARATION

Allow **TUF-TRAC®** to dry at least 8 hours before applying **TUF-TRAC® LINE STRIPING**. The surface must be thoroughly clean and dry.

APPLICATION

TUF-TRAC® LINE STRIPING may be applied with a brush or roller. Spray application is not recommended. Tennis courts should be striped according to U.S.L.T.A. Regulations for doubles play using a 2" stripe.

CLEANUP

Clean equipment with water.

COMPOSITION AND PHYSICAL PROPERTIES

Net Wt/Gal	11.3 - 12.0 lbs	Gloss	Flat
Solids	By Weight: 57-59.5% By Volume: 38% (Theoretical)	Storage Conditions	60°F to 80°F
Viscosity	95 ± 3 Ku @ 77°F	Recommended Coverage Rate*	1200 lineal ft./gal. @ 2" width @ 3 mils dry
Odor	Mild	Drying Time	Tack Free: 1/2 to 1 hour (@70°F, 50% humidity, adequate ventilation) Between Coats: 1 to 2 hours
Shelf Life	2 years in unopened containers	pH	9.5 - 10.5
Cleanup	Water	Coats Recommended	One
Color Stability	Exterior: Excellent Interior: Excellent	Freeze/Thaw Stability	DO NOT FREEZE

*Actual figures do not include spray loss. Also allow for surface irregularities and porosity, as well as material loss when mixing.



IMPORTANT NOTICE TO BUYER / WARRANTY AND LIMITATIONS ON OUR LIABILITY

We warrant our products to be free of manufacturing defects, and that they meet our current published physical properties and specifications. All information and suggestions presented are rendered gratis and is accurate to the best of our knowledge. They are based on technical data which we believe to be reliable, and are intended for use by persons having skill and "know-how," at their own discretion and risk. Prior to use, customers are cautioned to determine the suitability of our products for any given application through their own testing. **NO WARRANTY IS MADE, EXPRESS OR IMPLIED, REGARDING SUCH INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS OBTAINED FROM ITS USE OR THAT OUR PRODUCT SHALL BE MERCHANTABILITY OR FIT FOR ANY PARTICULAR PURPOSE.** SUCH STATEMENTS ARE NOT INTENDED TO SUGGEST INFRINGEMENT OF ANY PATENT. Since conditions of use of our products are beyond our control, all suggestions and statements are made without guarantee, warranty or other responsibility, express or implied, on our part. We assume no responsibility for results obtained, or damages incurred, from their use beyond replacing material proved to be defective or refunding the purchase price of such material at our option. Acceptance of delivery of our product means you have accepted the terms of this warranty, whether or not purchase orders or other documents state terms that vary from this warning. No seller is authorized to make any representations or warranty or assume any other liability on our behalf with any sales of our products. © 2/98 SANDSTROM PRODUCTS COMPANY 6/3/02