

# CLEAR WIRE LACQUER

**SERIES C863**  
**CLEAR LACQUER FOR BRAIDED WIRES**



PORT BYRON, IL 61275 • (309) 523-2121  
 1-800-747-1084 FAX # 1-309-523-3912

## DESCRIPTION

**Series C863 Clear Lacquer** is a quick drying lacquer designed for use over fiberglass, cotton, or other braided wire.

**TYPE:** Lacquer  
**COLORS:** Clear  
**FINISH:** Gloss  
**PACKAGING:** 55-gallon drums

## TYPICAL USES

**Series C863 Clear Lacquer** is designed for application over braided wire to prevent fraying of the ends, hold the braiding in place, and provide a smooth flexible glossy finish for easy feeding through slitting machines and for durability.

## CLEANUP

• Equipment may be cleaned with **Acetone**

## OUTSTANDING FEATURES/BENEFITS

- May be applied up to 150-feet per minute
- Fast drying
- Full gloss

## LIMITATIONS

- Applying at temperatures below 60°F can delay drying.
- For maximum productivity force drying is recommended. Use adequate ventilation in the oven to avoid dangerous solvent vapor buildup.

## APPLICATION

• **Series C863 is applied by a series of dip and wipes** until the desired appearance and feel is obtained. This normally takes three to six coats depending on the type of coater.

## COMPOSITION AND PHYSICAL PROPERTIES

**Net Weight/Gallon** 7.3 ± .2 lbs

**Theoretical VOC** 0.03 lbs/gallon (USA ONLY)  
 Contains acetone

**Theoretical Solids** By Weight: 32% ± 2%  
 By Volume: 23% ± 1%

**Storage Conditions** 30°F - 100°F

**Thinner/Cleanup** Acetone

**Shelf Life** 1 Year

[www.sandstromproducts.com](http://www.sandstromproducts.com)

### IMPORTANT NOTICE TO BUYER / WARRANTY AND LIMITATIONS ON OUR LIABILITY

We warrant our products to be free of manufacturing defects, and that they meet our current published physical properties and specifications. All information and suggestions presented are rendered gratis and is accurate to the best of our knowledge. They are based on technical data which we believe to be reliable, and are intended for use by persons having skill and "know-how," at their own discretion and risk. Prior to use, customers are cautioned to determine the suitability of our products for any given application through their own testing. **NO WARRANTY IS MADE, EXPRESS OR IMPLIED, REGARDING SUCH INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS OBTAINED FROM ITS USE OR THAT OUR PRODUCT SHALL BE MERCHANTABLE OR FIT FOR ANY PARTICULAR PURPOSE.** SUCH STATEMENTS ARE NOT INTENDED TO SUGGEST INFRINGEMENT OF ANY PATENT. Since conditions of use of our products are beyond our control, all suggestions and statements are made without guarantee, warranty or other responsibility, express or implied, on our part. We assume no responsibility for results obtained, or damages incurred, from their use beyond replacing material proved to be defective or refunding the purchase price of such material at our option. Acceptance of delivery of our product means you have accepted the terms of this warranty, whether or not purchase orders or other documents state terms that vary from this warning. No seller is authorized to make any representations or warranty or assume any other liability on our behalf with any sales of our products. © 2/98 SANDSTROM PRODUCTS COMPANY 2/2004